

# Molecular Simulation of Heat Shields




Savio J. Poovathingal<sup>1</sup>, Eric C. Stern<sup>2</sup>, Thomas E. Schwartzentruber, Graham V. Candler. <a href="mailto:1poova002@umn.edu">1poova002@umn.edu</a>, <a href="mailto:2eric.c.stern@nasa.gov">2eric.c.stern@nasa.gov</a>

Molecular simulations are used to understand and model detailed physical processes occurring in both, porous and non-porous ablating heat shields. The microstructural surface of a real heat shield sample is obtained through 3D reconstruction using X-ray micro tomography and then used in the Direct Simulation Monte Carlo (DSMC) solver Molecular Gas Dynamics Simulator [1] to perform molecular simulations.

The goal of such molecular modeling is to understand ablation physics at the most fundamental level, in order to reduce uncertainty margins on heat shield and to design better thermal protection systems for future hypersonic missions.

## X-ray computed tomography and surface grid for simulations

X-ray computed tomography (X-ray CT) is used to generate a 3D image of the inside of the object from a large series of two-dimensional radiographic images taken around a single axis of rotation [2].








Illustration of the reconstruction of a 3D surface from the 2D slices from tomography.




Demonstration of the robust cut-cell applied to algorithm [3] porous obtained from microstructure microtomography.




### Atomistic analysis of carbon based heat shields


Atomistic analysis provides detailed data on the chemical reactions occurring on a carbon surface. The analysis is aided through experiments [4] and SEM images. The molecular beam data is used as input for DSMC boundary conditions to propose oxidation model for full vehicle CFD simulations.



### Flow study at the micro scale using DSMC

DSMC simulations are performed using the real surface and reaction chemistry data from beam experiments.





DSMC simulations of flow over the real C-C composite. CO<sub>2</sub> production is observed due to gas phase reactions [5] within the gaps of the fibers despite CO being the dominant product at the atomistic scale. Higher mass loss is observed due to such gas-phase reactions.

# x[m]0.0005

U-velocity contours from a DSMC Simulation of driven flow through FiberForm. Surface generated using data from microtomography contains over 6 million triangular surface elements.

#### References

1) Nompelis I., Schwartzentruber T.E., AIAA 2013-1204.

2) Stern E. et. al., AIAA 2015-1450.

3) Zhang C., Schwartzentruber T.E., Computers and Fluids, Vol. 69, 2012.

4) Murray et. al., J. Phys. Chem C., Web Publication Mar 26 2015.

5)Poovathingal et. al., AIAA 2015-1449.

#### Acknowledgments

The authors would like to thank Dr. Brian Bagley for X-ray computed tomography, Vanessa J. Murray and Prof. Tim Minton for the molecular beam data and Prof. Erica Corral for the C-C composite sample. Dr. Stern's was supported through a NASA Space Technology Research Fellowship.